

ASA-X

ASA-X is our highly modified “industrial-grade” ASA filament with many features like UV resistance, zero warp technology and excellent mechanical properties. ASA-X is the perfect replacement when you require a performance material without the problems that can arise during printing with, for example, ABS. ASA-X not only has great strength and interlayer adhesion but also features one of the best aesthetics possible with FDM 3D printing. The reliable bed adhesion will ensure a smooth printing experience. ASA-X is perfect when you are looking for beautiful and strong prints that also last outside.


Material features:

- UV / Weather resistant
- Zero warp technology
- Excellent interlayer adhesion
- Great strength & aesthetics
- Reliable bed adhesion (Glass, tape & other adhesives)



Colours:

ASA-X is available from stock in 7 industrial colours. Other colours on request



Packaging:

ASA-X is available in nearly any type of packaging and labelling. Ask our team to help you customizing your product.

Filament specs.

Size	Ø tolerance	Roundness
1,75mm	± 0,05mm	≥ 95%
2,85mm	± 0,10mm	≥ 95%

Material properties

Description	Testmethod	Typical value
Specific gravity	ISO 1183	1,14 g/cc
MFR 220°C/10 kg	ISO 1133	13,7 gr/10 min
Tensile strength at yield	ISO 527	46,4 Mpa
Tensile strength at break	ISO 527	29,8 MPa
Elongation strain at break	ISO 527	16,2%
Elongation strain at yield	ISO 527	3,6%
Tensile (E) modulus	ISO 527	2090 MPa
Impact strength - Charpy notched 23°C	ISO 179	15,6 kJ/m2
Printing temp.	Internal method	240±10°C
Melting temp.	ISO 294	230±10°C
Vicat softening temperature	ISO 306	98°C

Additional info:

Recommended temperature for heated bed is ± 80-90°C. ASA-X is printed at high temperatures to make the final product extra strong. ASA-X can be used on all common desktop FDM or FFF technology 3D printers.

Storage: Cool and dry (15-25°C). This enhances the shelf life significantly.

The values presented in this publication are based on MCPP's knowledge and experience and are intended for reference purposes only. While MCPP has made every reasonable effort to ensure the accuracy of the information in this publication, MCPP does not guarantee that it is error-free, nor does MCPP make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. MCPP reserves the right to make any adjustments to the information contained herein at any time without notice. MCPP expressly disclaims warranties of any kind regarding the information contained herein, including, but not limited to, any warranties of merchantability or fitness of a particular purpose, use or application. MCPP shall not be liable for any damage, injury or loss induced from the use of MCPP's products in any application. Each user should thoroughly review this publication before selecting a product and, in view of the many factors that may affect processing and application of the product, each user should carry out their own investigations and tests and determining the safety, lawfulness, technical suitability, proprietary rights, and disposal/ recycling practices of the materials for the intended application.