



Kimya ABS-ESD 3D Filament

The Kimya **ABS-ESD** 3D filament belongs to the styrenic polymer family. **ABS-ESD** is an Acrylonitrile Butadiene Styrene to which an additive has been added to give it Electro Static Discharge properties: this material protects against electrostatic discharge. It also provides good impact resistance. It is a lightweight and rigid material that is also easy to print. It is ideal for applications requiring protection against electrostatic discharge. The Kimya ABS-ESD 3D filament has the following properties:

- Easy to print
- Protects against electrical discharge
- Complies with the **RoHS** and **REACH standards**

2-year ARMOR warranty.

FILAMENT PROPERTIES

PROPERTIES	TEST METHODS	VALUES
Diameter	INS-6712	1,75 ± 0,1 mm 2,85 ± 0,1 mm
Density	ISO 1183-1	1,03 g/cm ³
Moisture rate	INS-6711	< 0,5 %
Melt flow index (MFI)	ISO 1133-1 (@220°C – 10 kg)	15 - 20 g/10min
Glass transition temperature (Tg)	ISO 11357-1 DSC (10°C/min - 20-220°C)	107 °C

PRINT PARAMETERS AND SPECIMENS DIMENSIONS

PRINTING DIRECTION	XY
Printing Speed	40 mm/s
Infill	100% - rectilinear
Infill Angle	45°/-45°
Nozzle Temperature	260°C
Bed T°	100°C

PRINTED SPECIMENS PROPERTIES

	PROPERTIES	TEST METHODS	VALUES
MECHANICAL PROPERTIES	Tensile modulus	ISO 527-2/5A/50	1 121 MPa
	Tensile Strength	ISO 527-2/5A/50	24,3 MPa
	Tensile strain at strength	ISO 527-2/5A/50	3,1 %
	Tensile Stress at Break	ISO 527-2/5A/50	19,8 MPa
	Tensile strain at break (type A)	ISO 527	6,4 %
	Flexural modulus	ISO 178	856 MPa
	Flexural stress at conventional deflection (3,5% strain)*	ISO 178	27,3 MPa
	Deformation at Flexural Strength	ISO 178	0 %
	Charpy impact resistance	ISO 179-1/1eA	10,9 kJ/m ²
	Shore Hardness	ISO 868	66,7D
Note 1	*Fin de l'essai à 5% d'allongement d'après la norme ISO 178 même si l'éprouvette ne rompt pas.		
Note 2	Les données doivent être considérées comme des valeurs indicatives - Les propriétés peuvent être influencées par les conditions de production.		

Created on 10/09/2018 - Revised on 17/01/2022.