



TDS Rev 1.0

Technical Data Sheet: SimuBone™ Bone Simulation Filament

Physical Properties	Standard	Unit	Typical Value
Density	ISO 1183	g/cc	1.34

Mechanical Properties	Standard	Unit	Typical Value
Tensile Strength, Break	ISO 527	MPa	65
Tensile Modulus	ISO 527	MPa	3410
Tensile Elongation, Break	ISO 527	%	4
Flexural Strength	ISO 178	MPa	122
Flexural Modulus	ISO 178	MPa	3355

Thermal Properties	Standard	Unit	Typical Value
Glass Transition Temperature (Tg)	DSC	°C	55
Deflection Temperature at 0.45 MPa (66psi)	ISO 75	°C	89

Certifications	Standard	Efficacy Rate
Certified Antibacterial	ISO 22196:2011	99.9%

Printed Specimen Conditions
Printer: Open Source FDM/FFF
Nozzle: 0.4mm
Layer Height: 0.25mm
Infill: 100%, +/- 45°
Extrusion Temp: 230°C
Bed Temp: 23°C
Specimen Orientation: XY Flat

www.3dxtech.com

Disclaimer: The technical data contained on this data sheet is furnished without charge or obligation and accepted at the recipient's sole risk. This data should not be used to establish specifications limits or used alone as the basis of design. The data provided is not intended to substitute any testing that may be required to determine fitness for any specific use.